

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
4 September 2003 (04.09.2003)

PCT

(10) International Publication Number
WO 03/072246 A2

(51) International Patent Classification⁷: **B01J 23/66**,
35/10, 37/00, C07D 301/10, C07C 23/10, 213/04

(74) Agent: **LEMUTH, Richard, F.**; Shell Oil Company, 910
Louisiana Street, P.O. Box 2463, Houston, TX 77002-2463
(US).

(21) International Application Number: PCT/US03/05902

(22) International Filing Date: 25 February 2003 (25.02.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/360,060 25 February 2002 (25.02.2002) US

(71) Applicant (for all designated States except US): **SHELL
OIL COMPANY** [US/US]; 910 Louisiana Street, P.O. Box
2463, Houston, TX 77002-2463 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **LOCKEMEYER,
John, Robert** [US/US]; 3403 Stoney Mist Drive, Sugar
Land, TX 77479 (US). **YEATES, Randall, Clayton**
[US/US]; 16310 Maple Downs Lane, Sugar Land, TX
77478 (US). **SZYMANSKI, Thomas** [US/US]; 2705
Blue Heron Drive, Hudson, OH 44236 (US). **REMUS,
Donald, James** [US/US]; 2901 Wexford Boulevard, Stow,
OH 44224 (US). **GERDES, William, Herman** [US/US];
7799 Ranett Avenue, Hudson, OH 44236 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,
SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI,
SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN,
GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.



WO 03/072246 A2

(54) Title: CATALYST AND A PROCESS USING THE CATALYST

(57) Abstract: A catalyst which comprises a carrier and silver deposited on the carrier, which carrier has a surface area of at least 1 m²/g, and a pore size distribution such that pores with diameters in the range of from 0.2 to 10 µm represent at least 70 % of the total pore volume and such pores together provide a pore volume of at least 0.27 ml/g, relative to the weight of the carrier; a process for the preparation of a catalyst which process comprises depositing silver on a carrier, wherein the carrier has been obtained by a method which comprises forming a mixture comprising: a) from 50 to 90 %w of a first particulate a-alumina having an average particle size (d₅₀) of from more than 10 up to 100 µm; and b) from 10 to 50 %w of a second particulate a-alumina having an average particle size (d₅₀) of from 1 to 10 µm; %w being based on the total weight of a-alumina in the mixture; and shaping the mixture into formed bodies and firing the formed bodies to form the carrier, and a process for the epoxidation of an olefin, which process comprises reacting an olefin with oxygen in the presence of a said catalyst.

CATALYST AND A PROCESS USING THE CATALYST

BACKGROUND OF THE INVENTION

5 The present invention relates to a catalyst and to the use of the catalyst in olefin epoxidation.

 In olefin epoxidations, catalyst performance may be assessed on the basis of selectivity, activity and stability of operation. The selectivity is the percentage of the
10 converted olefin yielding the desired olefin oxide. As the catalyst ages, the percentage of the olefin converted normally decreases with time and to maintain a constant level of olefin oxide production the temperature of the reaction is increased. However this adversely affects the
15 selectivity of the conversion to the desired olefin oxide. In addition, the equipment used can tolerate temperatures only up to a certain level so that it is necessary to terminate the reaction when the reaction temperature would reach a level inappropriate for the reactor. Thus the
20 longer the selectivity can be maintained at a high level and the epoxidation can be performed at an acceptably low temperature, the longer the catalyst charge can be kept in the reactor and the more product is obtained. Quite modest improvements in the maintenance of selectivity over long
25 periods yields huge dividends in terms of process efficiency.

 Olefin epoxidation catalysts comprise a silver component, usually with one or more further elements co-deposited therewith on a carrier. Carriers are typically
30 formed of a temperature resistant oxide such as α -alumina and in general higher purity has been found to correlate with better performance. However it has also been found for example that the presence of minor amounts of impurities in

the carrier such as alkali metals and some forms of silica can have a beneficial effect.

Intuitively it might also be considered that the higher the surface area of the carrier, the greater the area available for deposition of the silver and therefore the more effective the silver deposited thereon. However, this is generally found not to be the case and in modern catalysts the tendency is to use a carrier with a surface area of less than 1 m²/g.

10 SUMMARY OF THE INVENTION

The present invention teaches that the picture with respect to carrier surface area is significantly more complicated than was at first appreciated since the nature of the porosity of the carrier, in particular the pore size distribution and the pore volume provided by the pores which have a pore size within a defined range, has now been found to play a significant role. On this basis it was possible to prepare olefin epoxidation catalysts with excellent activity, selectivity and unusually prolonged retention of the activity and stability level. The carriers having an advantageous pore size distribution may be made from particulate materials which have specific particle sizes.

The present invention provides a catalyst which comprises a carrier and silver deposited on the carrier, which carrier has a surface area of at least 1 m²/g, and a pore size distribution such that pores with diameters in the range of from 0.2 to 10 µm represent at least 70 % of the total pore volume and such pores together provide a pore volume of at least 0.27 ml/g, relative to the weight of the carrier.

The invention also provides a process for the preparation of a catalyst which process comprises:

a) selecting a carrier which has a surface area of at

least 1 m²/g, and a pore size distribution such that pores with diameters in the range of from 0.2 to 10 µm represent at least 70 % of the total pore volume and such pores together provide a pore volume of at least 0.27 ml/g,

5 relative to the weight of the carrier, and

b) depositing silver on the carrier.

The invention also provides a process for the preparation of a catalyst which process comprises depositing silver on a carrier, wherein the carrier has been obtained
10 by a method which comprises forming a mixture comprising:

a) from 50 to 90 %w of a first particulate α-alumina having an average particle size (d₅₀) of from more than 10 up to 100 µm; and

b) from 10 to 50 %w of a second particulate α-alumina
15 having a d₅₀ of from 1 to 10 µm;

%w being based on the total weight of α-alumina in the mixture; and firing the mixture to form the carrier. In an embodiment, amongst others; the mixture may be shaped into formed bodies and the formed bodies are fired to form the
20 carrier. When the formed bodies are formed by extrusion, it may be desirable to include conventional burnout materials and/or extrusion aids, and an aqueous liquid, e.g. water, in the mixture.

Further, the invention provides a process for the
25 epoxidation of an olefin, which process comprises reacting an olefin with oxygen in the presence of a catalyst which comprises a carrier and silver deposited on the carrier, which carrier has a surface area of at least 1 m²/g, and a pore size distribution such that pores with diameters in the
30 range of from 0.2 to 10 µm represent at least 70 % of the total pore volume and such pores together provide a pore volume of at least 0.27 ml/g, relative to the weight of the carrier.

The invention also provides a process for the epoxidation of an olefin, which process comprises reacting an olefin with oxygen in the presence of a catalyst which has been obtained by a process which comprises depositing
5 silver on a carrier, wherein the carrier has been obtained by a method which comprises forming a mixture comprising:
a) from 50 to 90 %w of a first particulate α -alumina having a d_{50} of from more than 10 up to 100 μm ; and
b) from 10 to 50 %w of a second particulate α -alumina
10 having a d_{50} of from 1 to 10 μm ;
%w being based on the total weight of α -alumina in the mixture; and firing the mixture to form the carrier. In an embodiment, amongst others, the mixture may be shaped into formed bodies and the formed bodies are fired to form the
15 carrier. When the formed bodies are formed by extrusion, it may be desirable to include conventional burnout materials and/or extrusion aids, and an aqueous liquid, e.g. water, in the mixture.

The invention also provides a method of using an olefin
20 oxide for making a 1,2-diol, a 1,2-diol ether or an alkanolamine comprising converting the olefin oxide into the 1,2-diol, the 1,2-diol ether or the alkanolamine wherein the olefin oxide has been obtained by a process for the epoxidation of an olefin in accordance with this invention.

25 In accordance with the teaching of this invention, by maximizing the number of pores having a diameter in the range of 0.2 to 10 μm , in particular by minimizing the number of pores having a diameter greater than 10 μm , the catalyst is advantaged over catalysts where are prepared
30 from carriers which have a substantial number of pores having a diameter greater than 10 μm .

DETAILED DESCRIPTION OF THE INVENTION

"Surface area" as used herein is understood to refer to the surface area as determined by the BET (Brunauer, Emmett
5 and Teller) method as described in Journal of the American Chemical Society 60 (1938) pp. 309-316.

As used herein, water absorption is deemed to have been measured in accordance with ASTM C393, and water absorption is expressed as the weight of the water that can be absorbed
10 into the pores of the carrier, relative to the weight of the carrier.

The pore size distribution may be measured by a conventional mercury intrusion device in which liquid mercury is forced into the pores of a carrier. Greater
15 pressure is needed to force the mercury into the smaller pores and the measurement of pressure increments corresponds to volume increments in the pores penetrated and hence to the size of the pores in the incremental volume. As used herein, the pore size distribution and the pore volumes are
20 as measured by mercury intrusion to a pressure of 3.0×10^8 Pa using a Micromeritics Autopore 9200 model (130° contact angle, mercury with a surface tension of 0.473 N/m, and correction for mercury compression applied).

The average particle size, referred to herein as " d_{50} ",
25 is as measured by a Horiba LA900 particle size analyzer and represents a particle diameter at which there are equal spherical equivalent volumes of particles larger and particles smaller than the stated average particle size. The method includes dispersing the particles by ultrasonic
30 treatment, thus breaking up secondary particles into primary particles. This sonification treatment is continued until no further change in the d_{50} value is noticed, which

typically requires 5 minute sonification when using the Horiba LA900 particle size analyzer.

As used herein, pore volume (ml/g), surface area (m²/g) and water absorption (g/g) are defined relative to the weight of the carrier, unless stated otherwise.

Typically, the pore size distribution is such that pores with diameters less than 0.2 μm represent less than 10 % of the total pore volume. Typically, the pore size distribution is such that pores with diameters greater than 10 μm represent less than 20 %, in particular less than 15 %, of the total pore volume. Preferably, the pore size distribution is such that the pores with diameters in the range of from 0.2 to 10 μm represent more than 75 %, in particular more than 80 %, more preferably more than 85 %, most preferably more than 90 % of the total pore volume; the pores with diameters greater than 10 μm represent less than 12 %, in particular less than 10 %, more in particular less than 5 % of the total pore volume; and the pores with diameters less than 0.2 μm represent less than 7 %, in particular at most 5 %, and more in particular at most 4 % of the total pore volume.

Frequently, the pore size distribution is such that the pores with diameters in the range of from 0.2 to 10 μm represent less than 99.9 %, more frequently less than 99 % of the total pore volume; the pores with diameters greater than 10 μm represent more than 0.1 %, more frequently more than 0.5 % of the total pore volume; and the pores with diameters less than 0.2 μm represent more than 0.1 %, more frequently more than 0.5 % of the total pore volume.

Typically, the pores with diameters in the range of from 0.2 to 10 μm provide a pore volume of at least 0.28 ml/g, in particular at least 0.3 ml/g, more in particular at least 0.35 ml/g. Typically, the pores with

diameters in the range of from 0.2 to 10 μm provide a pore volume of at most 0.8 ml/g, more typically at most 0.7 ml/g, in particular at most 0.6 ml/g, more in particular at most 0.56 ml/g. In a preferred embodiment, the pores with
5 diameters in the range of from 0.2 to 10 μm provide a pore volume in the range of from 0.35 to 0.45 ml/g.

The total pore volume of the carrier may vary between wide ranges. Typically the total pore volume is at least 0.28 ml/g, in particular at least 0.30 ml/g, more in
10 particular at least 0.35 ml/g. Typically, the total pore volume is at most 0.8 ml/g, and more typically it is at most 0.7 ml/g, in particular at most 0.6 ml/g, more in particular at most 0.56 ml/g. In a preferred embodiment, the total pore volume of the carrier is in the range of from 0.35 to
15 0.45 ml/g.

The surface area of the carrier is at least 1 m^2/g . Typically, the surface area is at most 2.9 m^2/g . Preferably, the surface area is in the range of from 1 to 2.6 m^2/g , more preferably from 1.4 to 2.6 m^2/g , most
20 preferably from 1.6 to 2.2 m^2/g , for example from 1.6 to 2.0 m^2/g or from 1.8 to 2.2 m^2/g .

The water absorption of the carrier is typically at least 0.3 g/g, more typically at least 0.35 g/g. Frequently, the water absorption is at most 0.8 g/g, more
25 frequently at most 0.7 g/g, or at most 0.55 g/g. Preferably, the water absorption of the carrier is in the range of from 0.35 to 0.7 g/g, for example 0.39 g/g, or 0.41 g/g, or any value in the range of from 0.35 to 0.55 g/g, in particular 0.38 to 0.5 g/g or 0.40 to 0.55 g/g
30 or 0.48 to 0.55 g/g. A higher water absorption and a higher total pore volume are in favour in view of a more efficient deposition of silver and further elements, if any, on the carrier by impregnation. However, at a higher water

absorption and higher total pore volume, the carrier, or the catalyst made therefrom, may have lower crush strength.

The carrier may be based on a wide range of materials.

Such materials may be natural or artificial inorganic

5 materials and they may include refractory materials, silicon carbide, clays, zeolites, charcoal and alkaline earth metal carbonates, for example calcium carbonate. Preferred are refractory materials, such as alumina, magnesia, zirconia and silica. The most preferred material is α -alumina.

10 Typically, the carrier comprises at least 85 %w, more typically 90 %w, in particular 95 %w α -alumina, frequently up to 99.9 %w α -alumina.

Carriers may generally be made by firing particulate mineral components at an elevated temperature until the
15 particles sinter together. In general, firing is continued until the particles are bonded together, either by the formation of bond posts from any added bond material or through sintering, but preferably not beyond the point at which the water absorption of the carrier is reduced.

20 The water absorption of the carrier may suitably be controlled by the use of so-called burnout materials, and it is preferred to employ a burnout material when practicing this invention. Burnout materials are well known in the art (cf., for example, F F Y Wang (Ed.), "Treatise on Materials
25 Science and Technology", Volume 9, (New York, 1976), pp. 79-81; or J S Reed, "Introduction to the Principles of Ceramic Processing", (New York, 1988), pp. 152 ff.). The burnout materials may also be used to ensure the preservation of the structure during a green, i.e. unfired, phase of the carrier
30 preparation, for example the phase in which formed bodies are shaped, for example by extrusion. The burnout materials are removed during the firing. The use of burnout materials also allows more complete sintering without too great a

reduction in water absorption of the carrier. The burnout materials are typically finely divided solid organic materials that volatilize or burn, leaving as little residue as possible. The selection of the burnout material is
5 considered not to be of any criticality to the invention. Burnout materials may be selected from the group of carbohydrates, gums, flours, proteins, lignins, resins, waxes, alcohols, and esters.

It is also a common expedient to use a bond material,
10 i.e. a material which reduces the length of sintering time applied to bond the particles together, and it is preferred to employ such bond material when practicing this invention. It is advantageous that the bond material also forms a coating on at least a part of the carrier surface, which
15 makes the carrier surface more receptive. Suitable bond materials have been specified hereinafter.

It has been found that, suitably, alumina carriers for use in this invention may be made by a method which comprises forming a mixture comprising:

- 20 a) from 50 to 90 %w of a first particulate α -alumina having a d_{50} of from more than 10 up to 100 μm , in particular from 11 to 60 μm , more in particular from 12 to 40 μm ;
- b) from 10 to 50 %w of a second particulate α -alumina
25 having a d_{50} of from 1 to 10 μm , in particular from 2 to 6 μm ; and preferably in addition.
- c) a bond material;
- %w being based on the total weight of α -alumina in the mixture; and then shaping the mixture into formed bodies and
30 firing the formed bodies, typically at a temperature of from 1250 to 1500 $^{\circ}\text{C}$, to form the carrier.

The present method for making alumina carriers is well adapted to produce the carriers for use in this invention,

in view of the careful matching of large and small particles of the α -alumina components. The alumina particles are readily commercially available, or they may readily be made, for example, by subjecting more course materials to grinding and sieving operations. In an embodiment, the smaller particles may be prepared from the larger particles by grinding, and the ground and un-ground particles are then combined. In another embodiment, the desired mixture of large and small particles may be formed by grinding relatively large particles to the extent that the mixture of particles has the desired bimodal particle size distribution.

Typically, the first particulate α -alumina is employed in a quantity of from 65 to 75 %w, relative to the total weight of α -alumina in the mixture. Typically, the second particulate α -alumina is employed in a quantity of from 25 to 35 %w, relative to the total weight of α -alumina in the mixture.

In particular when the carrier is an α -alumina carrier, more in particular comprising at least 80 %w, 90 %w, or 95 %w α -alumina, it is preferred that the bond material is based on a silica-containing composition comprising a crystallization inhibitor, inhibiting the formation of crystalline silica-containing compositions. It is also preferred that the bond material provides a coating of a non-crystalline silica compound to the carrier surface.

Typically, silica-containing compositions for use as a bond material comprise an amorphous silica compound which may be, for example, a silica sol, a precipitated silica, an amorphous silica, or an amorphous alkali metal silicate or aluminasilicate. Typically, silica-containing compositions for use as a bond material may also comprise hydrated alumina. The crystallization inhibitor that is most

conveniently incorporated is an alkali metal compound, in particular a water soluble salt, such as a sodium or potassium salt.

A convenient bond material may comprise a mixture of
5 boehmite, ammonium silicate or silica sol, and a water soluble sodium salt. Similar effects can be achieved by incorporation of conventional ceramic bonds formulated to contain aluminosilicates and an alkali metal component.

When the carrier is an α -alumina carrier, more in
10 particular comprising at least 80 %w, 90 %w, or 95 %w α -alumina, it is preferred that the bond material is based on
a) from 1 to 10 %w, in particular 2 to 5 %w, of an alumina hydrate, calculated as aluminum oxide relative to the weight of the α -alumina;
15 b) from 0.1 to 1 %w, in particular 0.2 to 0.8 %w, of an amorphous silica compound, as specified hereinbefore, calculated as silicon oxide relative to the weight of the α -alumina; and
c) from 0.01 to 0.5 %w, in particular 0.05 to 0.3 %w, of
20 an alkali metal compound, calculated as the alkali metal oxide relative to the weight of the α -alumina.

In a preferred embodiment, the alumina carrier has an alumina content of at least 95 %w and may be made by a method which comprises forming a mixture comprising:

25 a) from 65 to 75 %w, relative to the total weight of α -alumina in the mixture, of a first particulate α -alumina having a d_{50} of from 10 to 60 μm , in particular from 12 to 40 μm ;
b) from 25 to 35 %w, relative to the total weight of α -
30 alumina in the mixture, of a second particulate α -alumina having a d_{50} of from 2 to 6 μm ;
c) from 2 to 5 %w of an alumina hydrate, calculated as aluminum oxide relative to the total weight of α -alumina in

the mixture;

d) from 0.2 to 0.8 %w of an amorphous silica compound, as specified hereinbefore, calculated as silicon oxide relative to the total weight of α -alumina in the mixture; and

5 e) from 0.05 to 0.3 %w, of an alkali metal compound, calculated as the alkali metal oxide relative to the total weight of α -alumina in the mixture;

and then shaping the mixture into formed bodies and firing the formed bodies at a temperature of from 1250 to 1500 °C

10 to form the carrier.

The preferred alumina hydrate is boehmite, though gibbsite, bayerite or diasporite may also be used.

Suitable alkali metals are, for example, lithium, sodium and potassium, or combination thereof. Suitable
15 alkali metal compounds are, for example, alkali metal carbonates, alkali metal acetates, alkali metal formates, alkali metal nitrates, and combinations thereof. Typically, the overall atomic ratio of silicon to the alkali metal is in the range of from 1 to 10, more typically 2 to 8, for
20 example 6. The overall atomic ratio of silicon to the alkali metal is deemed to relate to the total alkali metal content and the total silicon content of the carrier, which includes any alkali metal and any silicon which may be present in the carrier other than in the bond material.

25 It is also preferred that the carrier particles be prepared in the form of formed bodies, the size of which is in general determined by the dimensions of a reactor in which they are to be deposited. Generally however it is found very convenient to use particles such as formed bodies
30 in the form of powdery particles, trapezoidal bodies, cylinders, saddles, spheres, doughnuts, and the like. The cylinders may be solid or hollow, straight or bend, and they

may have their length and cross-sectional dimensions about the same and from 5 to 10 mm.

The formed bodies can be formed from the mixture by any convenient molding process, such as spraying, spray drying, agglomeration or pressing, but preferably they are formed by extrusion of the mixture. For applicable methods, reference may be made to, for example, US-A-5145824, US-A-5512530, US-A-5384302, US-A-5100859 and US-A-5733842, which are herein incorporated by reference. To facilitate such molding processes, in particular extrusion, the mixture may suitably be compounded with up to about 30 %w and preferably from 2 to 25 %w, based on the weight of the mixture, of extrusion aids. Extrusion aids (also referred to by the term "processing aids") are known in the art (cf., for example, "Kirk-Othmer Encyclopedia of Chemical Technology", 4th edition, Volume 5, pp. 610 ff.). Suitable extrusion aids may be for example petroleum jelly, hydrogenated oil, synthetic alcohol, synthetic ester, glycol, polyolefin oxide or polyethylene glycol. Burnout materials are typically applied in a quantity of up to 30 %w, in particular from 2 to 25 %w, relatively to the weight of the mixture. Boric acid may also be added to the mixture, for example in a quantity of up to 0.5 %w, more typically in a quantity of from 0.01 to 0.5 %w. The effect of the presence of boric acid may be a reduced content of leachable alkali metal ions in the carrier after firing. Enough water may be added to the mixture to make the mixture extrudable (by the term "the weight of the mixture", as used hereinbefore, is meant the weight of the total mixture, but excluding the weight of any added water).

The formed bodies are dried and fired at a temperature high enough to ensure that the alumina particles are joined together by a sintering action and/or by the formation of

bond posts formed from the bond material, if incorporated in the mixture. Generally, drying may take place between 20 and 400 °C and preferably between 30 and 300 °C, typically for a period of up to 100 hours and preferably for from 5 minutes to 50 hours. Typically, drying is performed to the extent that the mixture contains less than 2 %w of water. Generally, firing may take place between 1250 and 1500 °C, typically between 1250 and 1470 °C, preferably between 1300 and 1450 °C, more preferably between 1300 and 1440 °C, typically for a period of up to about 5 hours and preferably for from 2 to 4 hours. Drying and firing may be carried out in any atmosphere, such as in air, nitrogen, or helium, or mixtures thereof. Preferably, in particular when the formed bodies contain organic material, the firing is at least in part or entirely carried out in an oxidizing atmosphere, such as in oxygen containing atmosphere.

It has been found that the performance of the catalyst may be enhanced if the carrier is washed, to remove soluble residues, before deposition of other catalyst ingredients on the carrier. On the other hand, unwashed carriers may also be used successfully. A useful method for washing the carrier comprises washing the carrier in a continuous fashion with hot, demineralised water, until the electrical conductivity of the effluent water does not further decrease. A suitable temperature of the demineralised water is in the range of 80 to 100 °C, for example 90 °C or 95 °C. Reference may be made to WO-00/15333 and US-B-6368998, which are incorporated herein by reference.

Generally, the catalyst of this invention comprises silver as a catalytically active metal. Appreciable catalytic activity is obtained by employing a silver content of the catalyst of at least 10 g/kg, in particular at least 50 g/kg, relative to the weight of the catalyst. The

preparation of the catalysts is known in the art and the known methods are applicable to the preparation of the catalyst of this invention. Methods of preparing the catalyst include impregnating the carrier with a silver
5 compound and performing a reduction to form metallic silver particles. Reference may be made, for example, to US-A-5380697, US-A-5739075, US-B-6368998, US-2002/0010094 A1, EP-A-266015, WO-00/15333, WO-00/15334 and WO-00/15335, which are incorporated herein by reference.

10 The impregnation may include impregnation with a solution of which the pH has a value above 12, for example 13 or 13.2 or above. This may be accomplished by the addition of a base to the impregnation solution, for example lithium hydroxide, cesium hydroxide or a tetraalkylammonium
15 hydroxide, such as tetramethylammonium hydroxide or tetraethylammonium hydroxide, in sufficient quantity. Dependent of the composition of the impregnation solution, a quantity of base in the range of from 20 to 70 mmole/kg catalyst, for example 30, 40, 50 or 60 mmole/kg catalyst may
20 be sufficient to achieve a sufficiently high pH.

The reduction of cationic silver to metallic silver may be accomplished during a step in which the catalyst is dried, so that the reduction as such does require a separate process step. This may be the case if the impregnation
25 solution comprises a reducing agent, for example, an oxalate, as described in the Examples hereinafter.

The catalyst preferably comprises silver, and a further element or compound thereof. Eligible further elements may be selected from the group of nitrogen, sulfur, phosphorus,
30 boron, fluorine, Group IA metals, Group IIA metals, rhenium, molybdenum, tungsten, chromium, titanium, hafnium, zirconium, vanadium, thallium, thorium, tantalum, niobium, gallium and germanium and mixtures thereof. Preferably the

Group IA metals are selected from lithium, potassium, rubidium and cesium. Most preferably the Group IA metal is lithium, potassium and/or cesium. Preferably the Group IIA metals are selected from calcium and barium. Where

5 possible, the further element may suitably be provided as an oxyanion, for example, as a sulfate, borate, perrhenate, molybdate or nitrate, in salt or acid form.

It is preferred to employ the carrier of this invention in the preparation of a highly selective catalyst. The

10 highly selective silver-based catalysts may comprise, in addition to silver, one or more of rhenium, molybdenum, tungsten, a Group IA metal, and a nitrate- or nitrite-forming compound, which may each be present in a quantity of from 0.01 to 500 mmole/kg, calculated as the element

15 (rhenium, molybdenum, tungsten, the Group IA metal or nitrogen) on the total catalyst. The nitrate- or nitrite-forming compounds and particular selections of nitrate- or nitrite-forming compounds are as defined hereinafter. The nitrate- or nitrite-forming compound is in particular a

20 Group IA metal nitrate or a Group IA metal nitrite. Rhenium, molybdenum, tungsten or the nitrate- or nitrite-forming compound may suitably be provided as an oxyanion, for example as a perrhenate, molybdate, tungstate or nitrate, in salt or acid form.

25 Of special preference are the highly selective catalysts which comprise rhenium in addition to silver. Such catalysts are known from EP-A-266015, US-A-4761394 and US-A-4766105, which are incorporated herein by reference. Broadly, they comprise silver, rhenium or compound thereof,

30 the further element (as defined hereinbefore, in particular tungsten, molybdenum and/or a Group IA metal, in particular lithium and/or cesium) other than rhenium or compound thereof, and optionally a rhenium co-promoter. The rhenium

co-promoter may be selected from one or more of sulfur, phosphorus, boron, and compounds thereof.

Preferred amounts of the components of the catalysts are, when calculated as the element, relative to the weight
5 of the catalyst:

- silver from 10 to 500 g/kg,
- rhenium from 0.01 to 50 mmole/kg, if present,
- the further element or elements, if present, each from 0.1 to 500 mmole/kg, and,
- 10 - the rhenium co-promoter from 0.1 to 30 mmole/kg, if present.

With respect to silver, this metal is present preferably in an amount of 50 to 500 g/kg, more preferably 50 to 400 g/kg, in particular 50 to 250 g/kg, for example
15 105 g/kg, or 120 g/kg, or 145 g/kg, or 191 g/kg, or 200 g/kg. Rhenium may preferably be present in an amount of from 0.1 to 10 mmole/kg, for example 2 mmole/kg, or 3 mmole/kg, or 5 mmole/kg. The further element or elements may each be present in a preferred amount of from
20 0.5 to 100 mmole/kg. For example, tungsten may typically be present in an amount in the range of from 0.5 to 20 mmole/kg, such as 1 mmole/kg, or 1.5 mmole/kg, or 5 mmole/kg, or 15 mmole/kg; molybdenum may typically be present in an amount in the range of from 1 to 40 mmole/kg,
25 such as 2.3 mmole/kg, or 12 mmole/kg, or 25 mmole/kg; and the alkali metal may each typically be present in amount of from 5 to 100 mmole/kg. Suitable amounts for lithium are for example 5 mmole/kg, or 10 mmole/kg, or 22.2 mmole/kg, or 30 mmole/kg, or 40 mmole/kg, or 50 mmole/kg. Suitable
30 amounts for cesium are for example 5 mmole/kg, or 5.3 mmole/kg, or 5.4 mmole/kg, or 7.2 mmole/kg, or 10.3 mmole/kg, or 10.5 mmole/kg, or 33 mmole/kg, or 47 mmole/kg.

Although the present epoxidation process may be carried out in many ways, it is preferred to carry it out as a gas phase process, i.e. a process in which the feed is contacted in the gas phase with the catalyst which is present as a solid material, typically in a packed bed. Generally the process is carried out as a continuous process.

The olefin for use in the present epoxidation process may be any olefin, such as an aromatic olefin, for example styrene, or a di-olefin, whether conjugated or not, for example 1,9-decadiene or 1,3-butadiene. Typically, the olefin is a monoolefin, for example 2-butene or isobutene. Preferably, the olefin is a mono- α -olefin, for example 1-butene or propylene. The most preferred olefin is ethylene.

The olefin concentration in the feed may be selected within a wide range. Typically, the olefin concentration in the feed will be at most 80 mole%, relative to the total feed. Preferably, it will be in the range of from 0.5 to 70 mole%, in particular from 1 to 60 mole%, on the same basis. As used herein, the feed is considered to be the composition which is contacted with the catalyst.

The present epoxidation process may be air-based or oxygen-based, see "Kirk-Othmer Encyclopedia of Chemical Technology", 3rd edition, Volume 9, 1980, pp. 445-447. In the air-based process air or air enriched with oxygen is employed as the source of the oxidizing agent while in the oxygen-based processes high-purity (at least 95 mole%) oxygen is employed as the source of the oxidizing agent. Presently most epoxidation plants are oxygen-based and this is a preferred embodiment of the present invention.

The oxygen concentration in the feed may be selected within a wide range. However, in practice, oxygen is generally applied at a concentration which avoids the flammable regime. Typically, the concentration of oxygen

applied will be within the range of from 1 to 15 mole%, more typically from 2 to 12 mole% of the total feed.

In order to remain outside the flammable regime, the concentration of oxygen in the feed may be lowered as the
5 concentration of the olefin is increased. The actual safe operating ranges depend, along with the feed composition, also on the reaction conditions such as the reaction temperature and the pressure.

A reaction modifier may be present in the feed for
10 increasing the selectivity, suppressing the undesirable oxidation of olefin or olefin oxide to carbon dioxide and water, relative to the desired formation of olefin oxide. Many organic compounds, especially organic halides and organic nitrogen compounds, may be employed as the reaction
15 modifier. Nitrogen oxides, hydrazine, hydroxylamine or ammonia may be employed as well. It is frequently considered that under the operating conditions of olefin epoxidation the nitrogen containing reaction modifiers are precursors of nitrates or nitrites, i.e. they are so-called
20 nitrate- or nitrite-forming compounds (cf. e.g. EP-A-3642 and US-A-4822900, which are incorporated herein by reference).

Organic halides are the preferred reaction modifiers, in particular organic bromides, and more in particular
25 organic chlorides. Preferred organic halides are chlorohydrocarbons or bromohydrocarbons. More preferably they are selected from the group of methyl chloride, ethyl chloride, ethylene dichloride, ethylene dibromide, vinyl chloride or a mixture thereof. Most preferred reaction
30 modifiers are ethyl chloride and ethylene dichloride.

Suitable nitrogen oxides are of the general formula NO_x wherein x is in the range of from 1 to 2, and include for example NO , N_2O_3 and N_2O_4 . Suitable organic nitrogen

compounds are nitro compounds, nitroso compounds, amines, nitrates and nitrites, for example nitromethane, 1-nitropropane or 2-nitropropane. In preferred embodiments, nitrate- or nitrite-forming compounds, e.g. nitrogen oxides and/or organic nitrogen compounds, are used together with an organic halide, in particular an organic chloride.

The reaction modifiers are generally effective when used in low concentration in the feed, for example up to 0.1 mole%, relative to the total feed, for example from 0.01 $\times 10^{-4}$ to 0.01 mole%. In particular when the olefin is ethylene, it is preferred that the reaction modifier is present in the feed at a concentration of from 0.1 $\times 10^{-4}$ to 50 $\times 10^{-4}$ mole%, in particular from 0.3 $\times 10^{-4}$ to 30 $\times 10^{-4}$ mole%, relative to the total feed.

In addition to the olefin, oxygen and the reaction modifier, the feed may contain one or more optional components, such as carbon dioxide, inert gases and saturated hydrocarbons. Carbon dioxide is a by-product in the epoxidation process. However, carbon dioxide generally has an adverse effect on the catalyst activity. Typically, a concentration of carbon dioxide in the feed in excess of 25 mole%, preferably in excess of 10 mole%, relative to the total feed, is avoided. A concentration of carbon dioxide as low as 1 mole% or lower, relative to the total feed, may be employed. Inert gases, for example nitrogen or argon, may be present in the feed in a concentration of from 30 to 90 mole%, typically from 40 to 80 mole%. Suitable saturated hydrocarbons are methane and ethane. If saturated hydrocarbons are present, they may be present in a quantity of up to 80 mole%, relative to the total feed, in particular up to 75 mole%. Frequently they are present in a quantity of at least 30 mole%, more frequently at least 40 mole%.

Saturated hydrocarbons may be added to the feed in order to increase the oxygen flammability limit.

The epoxidation process may be carried out using reaction temperatures selected from a wide range.

- 5 Preferably the reaction temperature is in the range of from 150 to 325 °C, more preferably in the range of from 180 to 300 °C.

- The epoxidation process is preferably carried out at a reactor inlet pressure in the range of from 1000 to 3500 kPa. "GHSV" or Gas Hourly Space Velocity is the unit volume of gas at normal temperature and pressure (0 °C, 1 atm, i.e. 101.3 kPa) passing over one unit volume of packed catalyst per hour. Preferably, when the epoxidation process is as a gas phase process involving a packed catalyst bed, the GHSV is in the range of from 1500 to 10000 Nl/(l.h). Preferably, the process is carried out at a work rate in the range of from 0.5 to 10 kmole olefin oxide produced per m³ of catalyst per hour, in particular 0.7 to 8 kmole olefin oxide produced per m³ of catalyst per hour, for example 5 kmole olefin oxide produced per m³ of catalyst per hour. As used herein, the work rate is the amount of the olefin oxide produced per unit volume of catalyst per hour and the selectivity is the molar quantity of the olefin oxide formed relative to the molar quantity of the olefin converted.

- 25 The olefin oxide produced may be recovered from the reaction mixture by using methods known in the art, for example by absorbing the olefin oxide from a reactor outlet stream in water and optionally recovering the olefin oxide from the aqueous solution by distillation. At least a portion of the aqueous solution containing the olefin oxide may be applied in a subsequent process for converting the olefin oxide into a 1,2-diol or a 1,2-diol ether.

The olefin oxide produced in the epoxidation process may be converted into a 1,2-diol, a 1,2-diol ether, or an alkanolamine. As this invention leads to a more attractive process for the production of the olefin oxide, it

5 concurrently leads to a more attractive process which comprises producing the olefin oxide in accordance with the invention and the subsequent use of the obtained olefin oxide in the manufacture of the 1,2-diol, 1,2-diol ether, and/or alkanolamine.

10 The conversion into the 1,2-diol or the 1,2-diol ether may comprise, for example, reacting the olefin oxide with water, suitably using an acidic or a basic catalyst. For example, for making predominantly the 1,2-diol and less 1,2-diol ether, the olefin oxide may be reacted with a ten fold
15 molar excess of water, in a liquid phase reaction in presence of an acid catalyst, e.g. 0.5-1.0 %w sulfuric acid, based on the total reaction mixture, at 50-70 °C at 1 bar absolute, or in a gas phase reaction at 130-240 °C and 20-40 bar absolute, preferably in the absence of a catalyst.
20 If the proportion of water is lowered the proportion of 1,2-diol ethers in the reaction mixture is increased. The 1,2-diol ethers thus produced may be a di-ether, tri-ether, tetra-ether or a subsequent ether. Alternative 1,2-diol ethers may be prepared by converting the olefin oxide with
25 an alcohol, in particular a primary alcohol, such as methanol or ethanol, by replacing at least a portion of the water by the alcohol.

The conversion into the alkanolamine may comprise, for example, reacting the olefin oxide with ammonia. Anhydrous
30 or aqueous ammonia may be used, although anhydrous ammonia is typically used to favour the production of monoalkanolamine. For methods applicable in the conversion of the olefin oxide into the alkanolamine, reference may be

made to, for example US-A-4845296, which is incorporated herein by reference.

The 1,2-diol and the 1,2-diol ether may be used in a large variety of industrial applications, for example in the fields of food, beverages, tobacco, cosmetics, thermoplastic polymers, curable resin systems, detergents, heat transfer systems, etc. The alkanolamine may be used, for example, in the treating ("sweetening") of natural gas.

Unless specified otherwise, the low-molecular weight organic compounds mentioned herein, for example the olefins, 1,2-diols, 1,2-diol ethers, alkanolamines and reaction modifiers, have typically at most 40 carbon atoms, more typically at most 20 carbon atoms, in particular at most 10 carbon atoms, more in particular at most 6 carbon atoms. As defined herein, ranges for numbers of carbon atoms (i.e. carbon number) include the numbers specified for the limits of the ranges.

Having generally described the invention, a further understanding may be obtained by reference to the following examples, which are provided for purposes of illustration only and are not intended to be limiting unless otherwise specified.

EXAMPLES

Preparation of Carriers

A carrier (designated hereinafter as "Carrier A") was made by mixing the following ingredients:

1. 67.4 parts by weight (pbw) of an α -alumina with d_{50} of 29 μm ;
2. 29 pbw of an α -alumina with d_{50} of 3 μm ;
3. 3 pbw of aluminum oxide (in the form of boehmite);
4. 0.5 pbw of silica (in the form of ammonia stabilized silica sol); and

5. 0.1 pbw of sodium oxide (in the form of sodium acetate).

To this mixture were added 5 %w, relative to the mixture weight, of petroleum jelly and 9 %w, relative to the mixture weight, of burnout material and 0.1 %w, relative to the mixture weight, of boric acid. Water (about 30 %w, relative to the mixture weight) was then added in an amount to make the mixture extrudable and this mixture was then extruded to form formed bodies in the form of hollow cylinders that are about 8 mm in diameter and 8 mm long. These were then dried and fired in a kiln at 1425 °C, for 4 hours in air to produce Carrier A. As regards procedures followed in this carrier preparation, reference may be made to US-A-5100859.

15 A second carrier (hereinafter "Carrier B") was made by the same procedure as Carrier A, except that 14 %w of burnout material was used, instead of 9 %w.

A third carrier (hereinafter "Carrier C") was made by the same procedure as Carrier A, except that:

- 20 - 20 pbw of the α -alumina with d_{50} of 3 μm was used instead of 29 pbw;
- 76.4 pbw of an α -alumina with d_{50} of 16 μm was used, instead of the α -alumina with d_{50} of 28 μm ;
- 8 %w of burnout material was used, instead of 9 %w; and
- 25 - 14 %w, relative to the mixture weight, of the petroleum jelly was used, instead of 5 %w.

For comparative purposes, an α -alumina was prepared according to the process as described in Example 1 of US-A-5100859 (hereinafter "Carrier D").

30 The carriers exhibited characteristics as indicated in Table I. The pore size distribution is specified as the volume fraction (%v) and the volume (ml/g) of the pores having diameters in the specified ranges (< 0.2 μm , 0.2-

10 μm , and $>10 \mu\text{m}$), relative to the total pore volume.

"Pore volume" represents the total pore volume.

TABLE I

Carrier	Surface area (m ² /g)	Water absorption (g/g)	Pore volume (ml/g)	Pore size distribution		
				<0.2 μm (%v)	0.2- 10 μm (%v; ml/g)	>10 μm (%v)
A	2.04	0.42	0.41	5	92; 0.37	3
B	2.11	0.49	0.42	9	72; 0.30	19
C	2.51	0.55	0.56	3	95; 0.53	2
D *)	0.73	0.40	0.40	< 1	64; 0.26	36
*) comparative						

Preparation of catalysts

A silver-amine-oxalate stock solution was prepared by
5 the following procedure:

415 g of reagent-grade sodium hydroxide were dissolved
in 2340 ml de-ionized water and the temperature was adjusted
to 50 °C.

1699 g high purity "Spectropure" silver nitrate was
10 dissolved in 2100 ml de-ionized water and the temperature
was adjusted to 50 °C.

The sodium hydroxide solution was added slowly to the
silver nitrate solution, with stirring, while maintaining a
solution temperature of 50 °C. This mixture was stirred for
15 15 minutes, then the temperature was lowered to 40 °C.

Water was removed from the precipitate created in the
mixing step and the conductivity of the water, which
contained sodium and nitrate ions, was measured. An amount

of fresh deionized water equal to the amount removed was added back to the silver solution. The solution was stirred for 15 minutes at 40 °C. The process was repeated until the conductivity of the water removed was less than 90 µmho/cm.

5 1500 ml fresh deionized water was then added.

630 g of high-purity oxalic acid dihydrate were added in approximately 100 g increments. The temperature was kept at 40 °C and the pH was kept above 7.8.

10 Water was removed from this mixture to leave a highly concentrated silver-containing slurry. The silver oxalate slurry was cooled to 30 °C.

699 g of 92 %w ethylenediamine (8% de-ionized water) was added while maintaining a temperature no greater than 30 °C. The resulting solution contained approximately 27-33
15 %w silver.

Enough 45 %w aqueous cesium hydroxide and water was added to this solution to give a finished catalyst having 14.5 %w silver and a cesium loading which provides the optimum selectivity. Actual cesium loadings have been
20 specified in Table II, hereinafter.

Carriers A, B and D, prepared as indicated under the heading "Preparation of Carriers", were impregnated with the impregnation solution and dried, as follows, to form Catalyst A (according to the invention), Catalyst B
25 (according to the invention) and Catalyst D (for comparison), respectively.

A carrier sample of approximately 30 g was placed under a 25 mm Hg vacuum for 1 minute at ambient temperature. Approximately 50 g of the impregnating solution was then
30 introduced to submerge the carrier, and the vacuum was maintained at 25 mm Hg for an additional 3 minutes. The vacuum was then released and the excess impregnating solution was removed from the catalyst pre-cursor by

centrifugation at 500 rpm for two minutes. The catalyst pre-cursor was then dried while being shaken at 250 °C for 5.5 minutes in a stream of air.

The catalysts were used to produce ethylene oxide from ethylene and oxygen. To do this, 1.5 to 2 g of crushed catalyst were loaded into a stainless steel U-shaped tube. The tube was immersed in a molten metal bath (heat medium) and the ends were connected to a gas flow system. The weight of catalyst used and the inlet gas flow rate (0.28 Nl/minute) were adjusted to give a gas hourly space velocity of 6800 Nl/(l.h), as calculated for un-ground bulk catalyst. The inlet gas pressure was 1530 kPa.

The gas mixture passed through the catalyst bed, in a "once-through" operation, during the entire test run including the start-up, consisted of 25 %v ethylene, 7 %v oxygen, 5 %v carbon dioxide, 63 %v nitrogen and 2.0 to 6.0 ppmv ethyl chloride.

The initial reactor temperature was 180 °C and this was ramped up at a rate of 10 °C per hour to 225 °C and then adjusted so as to achieve a constant ethylene oxide content of 1.5 %v in the outlet gas stream at an ethyl chloride concentration of 2.5 ppmv. Performance data at this conversion level are usually obtained when the catalyst has been on stream for a total of at least 1-2 days.

The initial performance values for selectivity and temperature are reported in Table II, below. A lower temperature needed to accomplish a certain ethylene oxide content in the outlet gas stream is indicative for a higher activity of the catalyst.

30

TABLE II

Catalyst	Cesium content (mmoles/kg)	Selectivity (%)	Temperature (°C)
A *)	5.4	82.5	224
B *)	5.3	81.9	232
D **)	3.0	81.9	240
*) invention			
**) comparative			

Additional catalysts may be obtained by impregnating separate samples of carrier C, such that the additional
5 catalysts contain, per kg of catalyst, for example, 191 g silver, 3 mmoles rhenium, 1.5 mmoles tungsten, 10.5 mmoles cesium and 40 mmoles lithium, or 200 g silver, 5 mmoles rhenium, 5 mmoles tungsten, 7.2 mmoles cesium and
22.2 mmoles lithium, or 145 g silver, 2 mmoles rhenium,
10 2.3 mmoles molybdenum, 10.3 mmoles cesium and 30 mmoles lithium. These catalysts may be used to produce ethylene oxide from ethylene and oxygen.

CLAIMS

1. A catalyst which comprises a carrier and silver deposited on the carrier in a quantity of at least 10 g/kg, relative to the weight of the catalyst, which carrier has a surface area of at least 1 m²/g, and a pore size distribution such that pores with diameters in the range of from 0.2 to 10 µm represent at least 70 % of the total pore volume and such pores together provide a pore volume of at least 0.27 ml/g, relative to the weight of the carrier.

2. A catalyst as claimed in claim 1 wherein the carrier has a pore size distribution such that the pores with diameters in the range of from 0.2 to 10 µm represent more than 75 % of the total pore volume and such pores together provide a pore volume of at least 0.28 ml/g, relative to the weight of the carrier; the pores with diameters greater than 10 µm represent less than 20 % of the total pore volume; and the pores with diameters less than 0.2 µm represent less than 10 % of the total pore volume.

3. A catalyst as claimed in claim 2 wherein the carrier has a pore size distribution such that the pores with diameters in the range of from 0.2 to 10 µm represent more than 90 % of the total pore volume and such pores together provide a pore volume of at least 0.3 ml/g, relative to the weight of the carrier; the pores with diameters greater than 10 µm represent less than 10 % of the total pore volume; and the pores with diameters less than 0.2 µm represent less than 7 % of the total pore volume.

4. A catalyst as claimed in any of claims 1-3 wherein the carrier has a total pore volume in the range of from 0.28 to 0.8 ml/g and a surface area of at most 2.9 m²/g, in particular the carrier has a total pore volume in the range

of from 0.3 to 0.7 ml/g and a surface area in the range of from 1 to 2.6 m²/g.

5. A catalyst as claimed in any of claims 1-4 wherein the carrier comprises at least 95 %w α -alumina and the carrier has a water absorption in the range of from 0.3 to 0.8 g/g and a surface area in the range of from 1.4 m²/g to 2.6 m²/g.

6. A catalyst as claimed in any of claims 1-5 wherein silver is deposited on the carrier in a quantity of from 50 to 500 g/kg, in particular 50 to 400 g/kg, more in particular 50 to 250 g/kg, relative to the weight of the catalyst.

7. A catalyst as claimed in any of claims 1-6 wherein the carrier comprises a bond material which is based on a silica-containing composition comprising an inhibitor for the formation of crystalline silica-containing compositions.

8. A catalyst as claimed in claim 7 wherein the carrier has an alumina content of at least 95 %w, and wherein the bond material is based on an alumina hydrate, an amorphous silica compound, and an alkali metal compound.

9. A catalyst as claimed in any of claims 1-8 which comprises, deposited on the carrier in addition to silver, one or more further elements selected from the group of nitrogen, sulfur, phosphorus, boron, fluorine, Group IA metals, Group IIA metals, rhenium, molybdenum, tungsten, chromium, titanium, hafnium, zirconium, vanadium, thallium, thorium, tantalum, niobium, gallium and germanium and mixtures thereof.

10. A catalyst as claimed in any of claims 1-9 which comprises, deposited on the carrier in addition to silver, one or more of rhenium, molybdenum, tungsten, a Group IA metal, and a nitrate- or nitrite-forming compound.

11. A catalyst as claimed in claim 9 or 10 wherein the Group IA metals are selected from lithium, potassium, rubidium and cesium.

12. A process for the preparation of a catalyst as
5 claimed in any of claims 1-11, which process comprises:
a) selecting a carrier which has a surface area of at least 1 m²/g, and a pore size distribution such that pores with diameters in the range of from 0.2 to 10 µm represent at least 70 % of the total pore volume and such pores
10 together provide a pore volume of at least 0.27 ml/g, relative to the weight of the carrier, and
b) depositing at least silver on the carrier in a quantity of at least 10 g/kg, relative to the weight of the catalyst.

13. A process for the preparation of a catalyst which
15 process comprises depositing silver on a carrier, wherein the carrier has been obtained by a method which comprises forming a mixture comprising:
a) from 50 to 90 %w of a first particulate α-alumina having an average particle size (d₅₀) of from more than 10
20 up to 100 µm; and
b) from 10 to 50 %w of a second particulate α-alumina having an average particle size (d₅₀) of from 1 to 10 µm; %w being based on the total weight of α-alumina in the mixture; and firing the mixture to form the carrier.

25 14. A process as claimed in claim 13, wherein the carrier has an alumina content of at least 95 %w, the mixture comprises:
a) from 65 to 75 %w, relative to the total weight of α-alumina in the mixture, of a first particulate α-alumina
30 having an average particle size (d₅₀) of from 11 to 60 µm;
b) from 25 to 35 %w, relative to the total weight of α-alumina in the mixture, of a second particulate α-alumina having an average particle size (d₅₀) of from 2 to 6 µm;

- c) from 2 to 5 %w of an alumina hydrate, calculated as aluminum oxide relative to the total weight of α -alumina in the mixture;
- d) from 0.2 to 0.8 %w of an amorphous silica compound,
- 5 calculated as silicon oxide relative to the total weight of α -alumina in the mixture; and
- e) from 0.05 to 0.3 %w of an alkali metal compound, calculated as the alkali metal oxide relative to the total weight of α -alumina in the mixture,
- 10 and the mixture is shaped into formed bodies and the formed bodies are fired at a temperature of from 1250 to 1500°C.

15 15. A process for the epoxidation of an olefin, which process comprises reacting an olefin with oxygen in the presence of a catalyst as claimed in any of claims 1-11, or in the presence of a catalyst which has been obtained by a process as claimed in any of claims 12-14.

16. A process as claimed in claim 15 wherein the olefin is ethylene.

20 17. A method of using an olefin oxide for making a 1,2-diol, a 1,2-diol ether or an alkanolamine comprising converting the olefin oxide into the 1,2-diol, the 1,2-diol ether or the alkanolamine wherein the olefin oxide has been obtained by a process for the epoxidation of an olefin as claimed in claim 15 or 16.

25

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
4 September 2003 (04.09.2003)

PCT

(10) International Publication Number
WO 2003/072246 A3

- (51) International Patent Classification⁷: **B01J 23/66**, 35/10, 37/00, C07D 301/10, C07C 29/10, 213/04
- (74) Agent: **LEMUTH, Richard, F.**; Shell Oil Company, 910 Louisiana Street, P.O. Box 2463, Houston, TX 77002-2463 (US).
- (21) International Application Number:
PCT/US2003/005902
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 25 February 2003 (25.02.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/360,060 25 February 2002 (25.02.2002) US
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant (*for all designated States except US*): **SHELL OIL COMPANY** [US/US]; 910 Louisiana Street, P.O. Box 2463, Houston, TX 77002-2463 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **LOCKEMEYER, John, Robert** [US/US]; 3403 Stoney Mist Drive, Sugar Land, TX 77479 (US). **YEATES, Randall, Clayton** [US/US]; 16310 Maple Downs Lane, Sugar Land, TX 77478 (US). **SZYMANSKI, Thomas** [US/US]; 2705 Blue Heron Drive, Hudson, OH 44236 (US). **REMUS, Donald, James** [US/US]; 2901 Wexford Boulevard, Stow, OH 44224 (US). **GERDES, William, Herman** [US/US]; 7799 Ranett Avenue, Hudson, OH 44236 (US).
- Published:
— with international search report
- (88) Date of publication of the international search report:
8 January 2004
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: SUPPORTED SILVER CATALYST AND AN EPOXIDATION PROCESS USING THE CATALYST

(57) Abstract: A catalyst which comprises a carrier and silver deposited on the carrier, which carrier has a surface area of at least 1 m²/g, and a pore size distribution such that pores with diameters in the range of from 0.2 to 10 µm represent at least 70 % of the total pore volume and such pores together provide a pore volume of at least 0.27 ml/g, relative to the weight of the carrier; a process for the preparation of a catalyst which process comprises depositing silver on a carrier, wherein the carrier has been obtained by a method which comprises forming a mixture comprising: a) from 50 to 90 %w of a first particulate a-alumina having an average particle size (d₅₀) of from more than 10 up to 100 µm; and b) from 10 to 50 %w of a second particulate a-alumina having an average particle size (d₅₀) of from 1 to 10 µm; %w being based on the total weight of a-alumina in the mixture; and shaping the mixture into formed bodies and firing the formed bodies to form the carrier, and a process for the epoxidation of an olefin, which process comprises reacting an olefin with oxygen in the presence of a said catalyst.

WO 2003/072246 A3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 03/05902

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B01J23/66 B01J35/10 B01J37/00 C07D301/10 C07C29/10
C07C213/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 908 343 A (BHASIN MADAN M) 13 March 1990 (1990-03-13) column 1, line 14 - line 41 column 14, line 7 - column 15, line 20 example E	1-12, 15, 16
X	EP 0 480 538 A (UNION CARBIDE CHEM PLASTIC) 15 April 1992 (1992-04-15) page 9, line 37 - line 58 examples	1-12, 15, 16
X	US 5 063 195 A (DI SHANG LIAN ET AL) 5 November 1991 (1991-11-05) comparative example 3	1-12, 15, 16
X	US 4 761 394 A (LAURITZEN ANN M) 2 August 1988 (1988-08-02) figure 7; table 1	1-12, 15, 16
-/-		



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

6 October 2003

Date of mailing of the international search report

24. 10. 03

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Besselmann, S

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 03/05902

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 845 296 A (AHMED MOINUDDIN ET AL) 4 July 1989 (1989-07-04) cited in the application the whole document ---	17
A	EP 0 496 470 A (SHELL INT RESEARCH) 29 July 1992 (1992-07-29) cited in the application ---	
X	WO 97 40932 A (NORTON CHEM PROCESS PROD) 6 November 1997 (1997-11-06) page 5, line 27 -page 6, line 2 page 9, line 8 -page 11, line 23 example 1 ---	13-16
A	US 3 664 970 A (MAIO DENNIS A DE) 23 May 1972 (1972-05-23) column 2, line 57 -column 4, line 27 -----	13-16

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 03/05902

Box I Observations where certain claims were found unsearchable (Continuation of Item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of Item 2 of first sheet)

This International Searching Authority found multiple inventions in this International application, as follows:

see additional sheet

1. ☒ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; It is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☒ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. Claims: 1-12,15-16 (PARTIALLY); 17

1.1. Claims: 1-12,15,16

Catalyst according to claims 1-11.

Process of preparing the catalyst as defined in claim 12.

Epoxidation process using the catalyst as defined in claims 15-16 (when referring to claims 1-11).

1.2. Claim : 17

Method of making a 1,2-diol, a 1,2-diolether or an alkanolamine as defined in claim 17

2. Claims: 13-16

Process for preparing a catalyst comprising depositing silver on a carrier comprising alpha alumina as defined in claims 13-14

Epoxidation process using the catalyst obtainable by the process of claim 13 as defined in claims 15-16 (when referring to claims 13-14).

Please note that all inventions mentioned under item 1, although not necessarily linked by a common inventive concept, could be searched without effort justifying an additional fee.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 03/05902

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4908343	A	13-03-1990	US 5057481 A	15-10-1991
EP 0480538	A	15-04-1992	JP 5305237 A	19-11-1993
			AT 170425 T	15-09-1998
			AU 656537 B2	09-02-1995
			AU 8576191 A	30-04-1992
			CA 2053411 A1	13-04-1992
			DE 69130098 D1	08-10-1998
			DE 69130098 T2	01-04-1999
			EP 0480538 A1	15-04-1992
			ES 2120412 T3	01-11-1998
			JP 2720124 B2	25-02-1998
			JP 4305246 A	28-10-1992
			KR 147853 B1	17-08-1998
			DK 480538 T3	02-11-1998
			US 6511938 B1	28-01-2003
US 5063195	A	05-11-1991	CN 1034678 A	16-08-1989
			DE 68921777 D1	27-04-1995
			DE 68921777 T2	23-11-1995
			EP 0327356 A1	09-08-1989
			IN 171804 A1	09-01-1993
			JP 1941314 C	23-06-1995
			JP 2056246 A	26-02-1990
			JP 6067475 B	31-08-1994
US 4761394	A	02-08-1988	AT 69977 T	15-12-1991
			AU 592478 B2	11-01-1990
			AU 8053987 A	05-05-1988
			BG 60854 B1	31-05-1996
			BR 8705810 A	31-05-1988
			CA 1304346 C	30-06-1992
			CN 87107194 A ,B	27-07-1988
			CS 8806977 A2	12-09-1990
			CS 8707729 A2	13-06-1990
			DD 267435 A5	03-05-1989
			DE 3774999 D1	16-01-1992
			DK 560087 A	01-05-1988
			EG 18719 A	30-12-1993
			EP 0266015 A1	04-05-1988
			ES 2028860 T3	16-07-1992
			FI 874786 A ,B,	01-05-1988
			GR 3003662 T3	16-03-1993
			HU 47046 A2	30-01-1989
			HU 202132 B	28-02-1991
			IE 60557 B1	27-07-1994
			IL 84232 A	21-06-1992
			IN 169589 A1	16-11-1991
			JP 2619660 B2	11-06-1997
			JP 63126552 A	30-05-1988
			KR 9611047 B1	16-08-1996
			MX 170627 B	31-08-1993
			NO 874528 A ,B,	02-05-1988
			NZ 222342 A	27-09-1989
			PH 25304 A	30-04-1991
			PL 268522 A1	08-12-1988
			PT 86038 A ,B	01-11-1987
			SG 126392 G	19-02-1993

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 03/05902

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4761394	A		SU 1831369 A3 TR 26675 A US 4833261 A YU 180088 A1 YU 197887 A1	30-07-1993 05-07-1994 23-05-1989 28-02-1990 31-12-1988
US 4845296	A	04-07-1989	NONE	
EP 0496470	A	29-07-1992	AU 641584 B2 AU 1034192 A BR 9200166 A CA 2059711 A1 CN 1063427 A ,B CS 9200166 A3 DE 69200450 D1 DE 69200450 T2 DK 496470 T3 EP 0496470 A1 ES 2061309 T3 JP 3302387 B2 JP 5084440 A KR 225874 B1 MX 9200243 A1 PL 293237 A1 SK 279174 B6 RU 2014114 C1 TR 25623 A US 5145824 A ZA 9200376 A	23-09-1993 30-07-1992 06-10-1992 23-07-1992 12-08-1992 12-08-1992 03-11-1994 23-02-1995 24-10-1994 29-07-1992 01-12-1994 15-07-2002 06-04-1993 15-10-1999 01-07-1992 02-11-1992 08-07-1998 15-06-1994 01-07-1993 08-09-1992 30-09-1992
WO 9740932	A	06-11-1997	AT 206636 T BR 9708889 A CA 2249277 A1 CN 1216939 A ,B DE 69707278 D1 DE 69707278 T2 DK 900126 T3 EP 0900126 A1 ES 2165601 T3 JP 3295433 B2 JP 11509777 T RU 2157729 C2 TW 482693 B WO 9740932 A1 US 5733842 A	15-10-2001 03-08-1999 06-11-1997 19-05-1999 15-11-2001 18-07-2002 11-02-2002 10-03-1999 16-03-2002 24-06-2002 31-08-1999 20-10-2000 01-04-2002 06-11-1997 31-03-1998
US 3664970	A	23-05-1972	NONE	